

Siro 7 Wall paint

DESCRIPTION	Water-borne, matt dispersion paint for interior painting. Very low side sheen.
PRODUCT FEATURES	Suitable for painting of new and already treated concrete, plaster, filler, plasterboard, chipboard and wood fibreboard surfaces according to instructions.
RECOMMENDED USES	Walls and ceilings in dry interior premises, e.g. living rooms, kitchens, offices and public spaces exposed to light wear.



TECHNICAL DATA



Base paints	A
Colour Range	Light colours tinted according to Tikkurila Symphony 2436 colour card.
Gloss grade	Matt
Building material emission class	M1
Coverage	For absorbing surfaces 5-7 m ² /l. For non-absorbing surfaces 9-11 m ² /l.
Can sizes	18 l
Thinner	Water
Application method	Roller, brush or spray. Airless spray: - nozzle 0,017" - 0,021" - thinning 0-10 vol.-%
Drying time at 23°C and 50% relative air humidity	Dust dry after half an hour. Recoatable after 1-2 hours.
Wet scrub resistance	SFS-EN 13300 class II, ISO 11998.
Heat resistance	85°C, ISO 4211-3.
Chemical resistance	Withstands cleaning chemicals and weak solvents, such as White Spirit.
Solids volume	approx. 38 % depending on the colour.
Density	1.3 kg/l, ISO 2811
Storage	Protect from frost. Store in dry and cool place, protected from sunlight. Tinted paint or opened can does not withstand long-term storage. Close the lid carefully for next use.
Product code	11V-s.

Siro 7 Wall paint

APPLICATION DETAILS

Application conditions	The surface to be painted must be dry, the temperature of the air at least +5 °C, and the relative humidity of the air below 80 %.
Preparation	Unpainted surfaces: Remove dirt and dust from the surfaces. Fill the surfaces with a suitable Tikkurila Presto or Prestonit filler, if needed, and sand the dried surface. Remove sanding dust. Prime with Siro 2 or Ykköspohja. Previously painted surfaces: Wash down previously painted surfaces with diluted Maalipesu cleaning detergent and rinse carefully with water. Sand hard, glossy and with alkyd paint painted surfaces matt and remove sanding dust. Fill cracks and holes with a suitable Tikkurila Presto or Prestonit filler and sand the dried surface. Remove sanding dust. Prime with Siro 2 or Ykköspohja, if needed.
Painting	Stir Siro 7 well before use and thin with water, if necessary. Apply 1-2 times with a roller, spray or brush.
Cleaning of tools	Remove the excess paint from tools before cleaning with water. Tikkurila Pensselipesu (Tool Cleaner) is recommended to be used for cleaning hardened paint.
Maintenance instructions	Cleaning earliest approx. 1 month after painting, if needed. The surfaces are cleaned with a dry brush or dust towel. Dirty surfaces are cleaned with a damp cleaning tool moistened in a neutral (pH 6-8) washing solution. The surface may not remain wet after cleaning. Follow the dilution instructions of the detergent manufacturer. The product achieves its final hardness and durability after one month under normal conditions, therefore the surfaces must be handled with care during this time. If the surfaces need to be cleaned soon after finishing, clean them gently with a dry or damp cleaning cloth.
Maintenance treatment	Surfaces painted with Siro 7 can be recoated with same type of water-borne paint. See preparation.
EU VOC 2004/42/EC-limit value	(cat A/a) 30g/l(2010) Siro 7 contains VOC max. 30g/l.

HEALTH AND SAFETY LABELLING according to Regulation (EC) No. 1272/2008

Contains 1,2-benzisothiazol-3(2H)-one and 5-chloro-2-methyl-2H-isothiazol-3-on/ 2-methyl-2H - isothiazol-3-one (3:1). May produce an allergic reaction. Wear protective gloves. A Safety Data Sheet is available on request _____

ENVIRONMENTAL and WASTE DISPOSAL	Empty cans should be recycled or disposed of in accordance with local regulations. Liquid waste should be destroyed according to the local regulations.
TRANSPORT	ADR: not classified

sre061113 / linla170613 / niar121113 / pih170613 / 11V-s

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.
